

DESCRIPTION: Exceeds performance requirements of ASTM D 3019, TYPE III.

PREPARATION: **Stelwagon Kure-A-Leke** Rubberized Coating is a professional grade, rubberized and polymer modified coating for sealing hairline cracks and small, hard to find leaks in low slope asphalt based roof systems. **Stelwagon Kure-A-Leke** Rubberized Coating provides excellent elongation and recovery properties, enhanced adhesive properties, improved cold temperature pliability and superior lap and bonding strength. **Stelwagon Kure-A-Leke** Rubberized Coating is also excellent for bonding gravel or ceramic granules to BUR roof systems and bonding modified ply and cap sheets. **Stelwagon Kure-A-Leke** Rubberized Coating eliminates burn hazards associated with hot kettles and propane torches, and is ideal where their use is prohibited.

NOTE: This product is formulated to be used on Asphalt Modified Roll Roofing Sheets as replacement for hot mop asphalt. Do not use on sheets which require torchdown or other techniques such as "Torching/Polyolefin Film," EDPM, PVC or other single ply membranes without approval of membrane manufacturer. For cracks and repairs other than hairline or pinholes, make repairs in accordance with good roofing practices using Stelco Cement and three course method of cement and web.

PREPARATION: All surfaces must have proper drainage and be clean, dry and free of surface rust and any other foreign matter. Make repairs to existing roof prior to application of this product including deck or structural repairs (according to building codes), and existing membrane repairs using Stelco Cement and reinforcing fabric. Always remove excessive particulate surfacing materials on modified membranes (sweeping with a stiff broom is recommended) prior to adhesive application. On re-roofing applications, severely weathered BUR membranes may require a pre-application of an Asphalt Primer.

MIX THOROUGHLY TO ENSURE PRODUCT UNIFORMITY. DO NOT HEAT OR THIN. DO NOT APPLY IF RAIN IS EXPECTED WITHIN 24 HOURS.

FOR BEST RESULTS: Apply when surface temperatures are between 50° and 120°F. In colder weather product should be stored in heated room (65° to 90°F) at least 24 hours prior to application. After a minimum of 45 days cure time, apply a reflective roof coating. This will greatly extend the life of the roof.

APPLICATION: For exterior use only. Productive clothing and eyewear should be used during application of this product. **Stelwagon Kure-A-Leke** Rubberized Coating applies easily with a roofing brush or notched squeegee. For adhesive application of membrane and ply sheets, apply a continuous film with sufficient amounts to cover all laps so that a small continuous bead can be seen at the lap edges. Roll in all laps and bonded areas with steel roller. Approximate coverage rate is 1-2 gallons per 100 sq. ft. per ply. For best results, cut the mod-bit sheets to a maximum of 18 ft. lengths and allow to relax on job site before application. For coating application, apply using roofing brush or notched squeegee at the rate of 3-5 gallons per square. Embed reinforcing fabric over hairline cracks or areas of concern. Do not apply to roofs with a pitch greater than ¼" in 12 pitch.

PRECAUTIONS: This product contains solvents. When working around ventilation units or HVAC equipment, ensure proper fume mitigation procedures are taken to avoid fumes and/or odors from entering air handling equipment and building. When transporting this product, ensure that lid is tight and pail secure and upright. Do not allow pail to tumble as this may cause lid to loosen and leakage to occur. Do not transport on passenger seats or inside the passenger compartment of any vehicle. Store product in the cargo area of vehicle, and secure over protective cloths to prevent damage due to accidental spills. Do not store at temperatures above 110° F. This manufacturer also disclaims liability for flat surface application where poor drainage or moisture may prevail. Do not reuse empty containers. Do not use in drinking water or food systems. Seal container when not in use.

CLEAN-UP: Clean tools with paint thinner or mineral spirits when not in use.

TYPICAL PHYSICAL & PERFORMANCE CHARACTERISTICS:

Weight Per Gallon	7.6 - 8.0 lbs
Solids by Weight	60 - 64%
Permeability (ASTM D1653)	< 5 Perms
Consistency	Squeegee, Brush or Roller
Surface Temperature	40 - 120 °F
Cure Time (50% Relative Humidity, 70°F)	4 - 8 hours
Full Cure (50% Relative Humidity, 70°F)	90 days
Flammability	105 °F
Clean-up Tools	Painter Thinner or Mineral Spirits

*Note: Percentages may vary + or - 10%

Approx. Shipping Weights: (Note: All approx. weights include container)

5 gallons (18.9L)	45lbs.
-------------------	--------

VOC/VOS - 300 g/l max. (2.5 lbs./gal.)

LIMITED WARRANTY AND DISCLAIMER: Stelwagon hereby warrants to the original purchaser, contingent upon original proof of purchase, that this product will be free from any and all manufacturing defects, at the time of purchase, that may materially and adversely affect the product's performance. Should a manufacturing defect materially and adversely affect this product's performance, Stelwagon shall, within its sole discretion and upon receipt of Purchaser's timely written notice within the Warranty Period, provide replacement product(s) or refund the purchase price of the defective product. THIS LIMITED WARRANTY IS PURCHASER'S EXCLUSIVE REMEDY AND SUPERCEDES AND IS EXPRESSLY IN LIEU OF ANY OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. This limited warranty does not cover labor or installation costs, areas with ponding water (as defined by the NRCA), consequential damages or incidental damages. Some states do not allow limitations on how long an implied warranty lasts, so the above limitation may not apply to you. This warranty gives you specific legal rights, and you may also have other rights which vary from state to state. Direct all warranty claims in writing, along with original proof of purchase, to Stelwagon, c/o Warranty Claims Department, 10096 Sandmeyer Lane, Philadelphia, PA 19116. The exclusive venue for any legal action arising out of the purchase of this product or this warranty shall be had in a court of competent jurisdiction within Philadelphia County, Pennsylvania. Pennsylvania law shall govern. For additional information, visit www.stelwagon.com.

©2014 Stelwagon Roofing Supply
 Manufactured for / Fabricado por: Stelwagon Roofing Supply
 10096 Sandmeyer Lane, Philadelphia, PA 19116